

PRODUCT TYPE

Water-borne, 2-component polyurethane parquet lacquer.

The product has been classified to **Group M1** in Emission Classification of building materials.

The product has been awarded the Key Flag Symbol (Avainlippu), marking Finnish origin.

Marine Equipment Approval (2014/90/EU) number MEDB0000355.

USAGE

OPAL 10 is suitable for roller and brush application on parquet and wooden floors. Designed for floors, which are subjected to severe wear stress, for example, sports halls and public premises. Complies with DIN 18032-2 and EN 14904 friction requirements for sports halls.

Not suitable for the lacquering of diamond pine and chemically treated wood, e.g., smoked oak.

TECHNICAL DATA**Mixing ratio**

Base	9 parts by volume
Hardener	1 part by volume

Pot life, +23 °C

6 h

Solids

About 27 % by volume

Volatile organic compound (VOC)

EU VOC limit value (kat A/i): 140 g/l.
The product's VOC: max. 140 g/l.

Practical spreading rate

One coat with lacquer roller or brush:	
One coat with steel trowel	8 - 10 m ² /l
(maintenance lacquering):	25 m ² /l

Density

abt. 1.0 g/ml

Drying time, +20°C / RH 50 %**- steel trowel application**

after 15 - 30 min

- lacquer roller or brush application

after abt. 2 - 4 h

- fit for light traffic

after 1 - 2 days

The drying process will be slower in cold and/or damp.

Thinner, clean up

Water. Wash the equipment immediately after use with water and RENSA BRUSH brush cleaner.

Finish

Matt

Colours

Clear

Packages

Lacquer (base): 4,5 L. Hardener: 0,5 L.

SAFETY MARKINGS

See Safety Data Sheet.

Surface preparation and application

The wood surface must be dry, well sanded and free from sanding dust and other dirt.

Untreated and clean-sanded surfaces:

Fill the gaps with GAP parquet putty. Prime the surface with Teknos primer lacquer according to the instructions. Intersand, if necessary, with sandpaper or an abrasive net n:o 150 after the first primer coat. Mix OPAL hardener and OPAL parquet lacquer together. Pour the hardener into the lacquer container. Shake the lacquer container vigorously for at least 30 seconds. Let the lacquer deaerate for 5–10 minutes. Finish with 2–3 coats of OPAL parquet lacquer using a lacquer roller or a paint brush along the grain of the wood. Do not close the container after the hardener has been added! (The reaction between the hardener and the lacquer produces small amounts of gas (carbon dioxide).)

Factory lacquered parquets or lacquered floors (maintenance lacquering):

Clean the floor thoroughly. Intersand gently by using sandpaper n:o 100–150.

Remove the sanding dust with a vacuum cleaner and finish with a clean damp cloth.

Apply one coat of OPAL parquet lacquer with a stainless steel trowel, and 1–2 coats with a lacquer roller or a brush. Note! If wax has been used for floor care ensure the compatibility with the maintenance lacquer beforehand by consulting the producers. If the floor has previously been treated with oil, urethane or alkyd lacquer, the floor must be sanded to bare wood before lacquering.

If the second coat is not applied within 48 hours after the first coat, intersand the floor gently. Ensure that the previous lacquer coat has fully dried before applying a new one. Always stir lacquer thoroughly before use.

Line paintings:

SUPERLATEKSI can be used for floor line paintings in sports hall floors. The paint is applied between lacquer coats. Lines can be painted also on the parquet primer.

Ensure the case-specific compatibility of the line paint and the lacquer beforehand.

Note! Some rubber types in carpets and anti-slip materials may contain plasticisers that can cause permanent damage to the surface and colour of the protective coat.

Application conditions

The surface to be varnished has to be dry.

The moisture content of the wood should be 7 ± 2 % by weight.

The temperature of the air, the surface and the lacquer shall be above +18 - 24°C and the relative humidity of the air 40 - 60% during the time of application and drying.

Care instructions

The varnished surface reaches its final hardness and washability within 2 weeks.

Rough handling and washing is to be avoided during this period. Stained surfaces can be cleaned with a moist cleaning cloth or mop. Use a neutral detergent. Very dirty surfaces can later be cleaned with a slightly alkaline universal washing detergent.

ADDITIONAL INFORMATION

Storage time: in unopened containers, above +1°C, for 1 year.
MUST NOT FREEZE.



EN_2299_Tuoteseloste.pdf